



DATA SHEET

Innovative Magnesia Alumina Chrome Brick			
Item NO		RT-MAGe-80	RT-MAGe-75
Physical Property:			
Apparent Porosity(%)	≤	17	18
Cold Crushing Strength(MPa)	≥	50	50
Refractoriness Under Load(T0.6 °C)	≥	1700	1650
Thermal Shock Resistance (950°C,Air Cooling)(Cycles)	≥	70	70
Chemical Analysis(%)			
MgO	≥	80	75
Cr2O3	*	3-5	3-5
Al2O3	*	8-12	8-12
Note:All data are average values obtained at samples for laboratory purposes.			

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD:26km away from Zhengzhou International Airport,
Zhengzhou 451100,Henan, China

Tel:0086-371-62586888 Fax:0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com