



DATA SHEET

Fused Rebonded Magnesia Chromite Brick								
Item NO		RT-FRM Ge-12	RT-FRM Ge-14	RT-FRM Ge-16	RT-FRM Ge-18	RT-FRM Ge-20	RT-FRM Ge-22	RT-FRM Ge-26
Physical Property:								
Bulk Density(g/cm3)	≥	3	3.05	3.08	3.1	3.15	3.2	3.25
Apparent Porosity(%)	≤	16	16	16	16	16	16	16
Cold Crushing Strength(MPa)	≥	50	50	50	50	50	50	50
Refractoriness Under Load(T0.6 °C)	≥	1700	1700	1700	1700	1700	1700	1700
Chemical Analysis(%)								
MgO	≥	68	65	60	58	55	50	45
Cr2O3	≥	12	14	16	18	20	22	26
SiO2	≤	1.2	1.4	1.4	1.5	1.5	1.5	1.5
Note:All data are average values obtained at samples for laboratory purposes.								

Henan Ruitai Refractory Materials Technology Co.,Ltd

ADD:26km away from Zhengzhou International Airport,
Zhengzhou 451100,Henan, China

Tel:0086-371-62586888 Fax:0086-671-62585779

Website: www.ruitairefractories.com Email: ruitairefractories@163.com